

SERIES 6680 MARQUISE

HIGH GLOSS POLYURETHANE FINISH



PRODUCT FEATURES

- Super tough finish
- VOC compliant
- Gloss finish
- Resistant to heavy traffic
- Resistant to cleaning compounds
- Easy to apply

GENERAL PROPERTIES

A heavy duty VOC compliant, oil-modified polyurethane, clear gloss coating. Dries to a super tough finish that is resistant to: heavy traffic, abrasion, rubber burns and cleaning compounds. For wood substrates only.

RECOMMENDED USES

- Wood floors
- Wood railings
- Wood gym floors
- Wood trim

LIMITATIONS

- Do not apply when air and surface temperature are below 60°F or above 90°F.

Finish	Gloss
Vehicle Type	Oil- modified polyurethane
Pigment Type	Not Applicable
Solvent Type	Mineral spirits
Coating Category	350 g/l max VOC
% Solid by Weight	59%
% Solid by Volume	53%
Weight/Per Gallon	7.62 lbs/ gal
Recommended Wet Film by Coat	3 mils per coat
Theoretical Coverage @ 1mil	860 sq ft. / gallon
Viscosity @ 77° F Zahn #2	18-22 sec
Dry Time Average	To touch: 6 hours
Application Method	T-bar, roller, brush
Shelf Life	2 Years
Packaged	One and five gallon pails
Flash Point	Above 100°F
Colors	Amber

SURFACE PREPARATION

All surfaces must be dry, thoroughly clean, free of loose paint, rust, dirt, oil, grease and all other foreign matter.

APPLICATION CONDITIONS

Do not apply over moisture or wet surfaces.
Air temperature must be between 60°F and 90°F for best results.

APPLICATION EQUIPMENT

T-bar
Roller
Brush

THINNING

Do not thin.

CLEAN UP INSTRUCTIONS

Use mineral spirits.

Keep out of reach of children.

Safety Data Sheets available upon request.

Keep from freezing.

HEALTH & SAFETY INFORMATION

Contains mineral spirits. Keep away from heat and open flame. To avoid breathing vapors or spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air or wear respiratory protection (NIOSH/MSHATC23C or equivalent), or leave the area. Close container after each use. Avoid prolonged contact with skin. Do not take internally.

ACCURACY OF DATA

The technical data presented above are true and accurate as of the date of issuance of this Mercury Paint data sheet and are subject to change without notice. We endeavor to supply all catalog holders with up-to-date catalog pages. Therefore, if the issue date is more than a year old, please inquire whether a new page has since been issued. Please visit www.mercurypaint.com for the newest version of this data sheet.

WARRANTY

This product is warranted only to conform to the analysis and specifications expressed above. No other warranty or guarantee, including its merchantability or suitability for any specific application, is implied. The liability of Mercury Paint Corporation, if any, is limited to replacement of product or refund of purchase price and excludes labor, cost of labor of other consequential damages, provided that the purchaser notifies management of Mercury Paint Corporation with twenty-four hours of the application of the product.

