

# SERIES 7500

## ALKYD EGGSHELL FINISH RUST PREVENTATIVE COATING



### PRODUCT FEATURES

- Decorative low luster finish
- Durable
- Interior/ Exterior
- Flexible
- Excellent weathering
- Rust preventative

### GENERAL PROPERTIES

A low odor, heavy duty, rust preventative eggshell enamel. Dries to a tough, washable, decorative finish.

### RECOMMENDED USES

- For metal substrates only
- Structural steel
- Doors
- Bucks
- Tanks
- Railings

### LIMITATIONS

- Not for immersion service.

<b>Finish</b>	Eggshell
<b>Vehicle Type</b>	Alkyd
<b>Pigment Type</b>	Titanium Dioxide & Ligh Fast Pigment
<b>Solvent Type</b>	Mineral Spirits
<b>Coating Category</b>	Rust Preventative coating- 400 g/l max
<b>% Solid by Weight</b>	75% minimum
<b>% Solid by Volume</b>	55% minimum
<b>Weight/Per Gallon</b>	11 lbs/gal avg
<b>Recommended Dry Film by Coat</b>	1.5 to 2.0 mils per coat
<b>Theoretical Coverage</b>	500-600 sq ft. / gallon
<b>Viscosity @ 77° F</b>	89-100 KU
<b>Dry Time Average</b>	To touch: 2-4 hours To recoat: 18 hours
<b>Application Method</b>	Brush, roller, spray
<b>Shelf Life</b>	2 Years
<b>Packaged</b>	One and five gallon pails
<b>Flash Point</b>	105°F
<b>Colors</b>	White and custom colors upon request
<b>Federal Specification</b>	TT-E-529F NYCTA TT-P-24D



### **SURFACE PREPARATION**

All surfaces must be dry, thoroughly clean, free of loose paint, rust, grease, oil and all other foreign matter.

### **APPLICATION CONDITIONS**

Temperature: 45°F.-100°F  
Relative humidity: up to 85%  
Surface temperature: 5°F above dew point

### **APPLICATION EQUIPMENT**

Brush – Good quality china bristle  
Roller – Any high quality roller  
Spray – Fluid pressure 2,000-2,500 PSI  
Tip- 0.15- 0.21 orifice

### **THINNING / CLEAN UP INSTRUCTIONS**

Do not thin. Clean up with xylene or mineral spirits.

### **ENVIRONMENTAL INFORMATION**

Contains no lead, mercury or chromate hazardous compounds. Complies with N.Y., N.J. and other states' requirements for limitation of volatile organic compounds. Meets New York Part 205 architectural surface coatings. Meets criteria for non-photochemical solvents in accordance with New York City Law 49.

**Keep out of reach of children.**

**Safety Data Sheets available upon request.**

**Keep from freezing.**

### **HEALTH & SAFETY INFORMATION**

**WARNING!** Combustible. Contains mineral spirits and aromatic naphtha. Keep away from heat and open flame. Do not take internally. May irritate eyes and skin. Prolonged breathing of vapors may irritate respiratory tract causing headache, nausea and dizziness. Use only with adequate ventilation. When ventilation is inadequate use respirator. Avoid contact with skin and breathing of vapors or spray mist. In case of eye contact, flush immediately with water. Close container tightly and wash hands properly after each use.

### **RECOMMENDED SYSTEMS**

<b>Ferrous Metal New</b>	Primer: Series 3000 Finish: Series 7500
<b>Ferrous Metal Repainted</b>	Primer: Series 3000 Finish: Series 7500
<b>Galvanized Metal New</b>	Primer: Series 3500 Finish: Series 7500
<b>Galvanized Metal Repainted</b>	Primer: Series 2000 Finish: Series 7500

### **ACCURACY OF DATA**

The technical data presented above are true and accurate as of the date of issuance of this Mercury Paint data sheet and are subject to change without notice. We endeavor to supply all catalog holders with up-to-date catalog pages. Therefore, if the issue date is more than a year old, please inquire whether a new page has since been issued. Please visit [www.mercurypaint.com](http://www.mercurypaint.com) for the newest version of this data sheet.

### **WARRANTY**

This product is warranted only to conform to the analysis and specifications expressed above. No other warranty or guarantee, including its merchantability or suitability for any specific application, is implied. The liability of Mercury Paint Corporation, if any, is limited to replacement of product or refund of purchase price and excludes labor, cost of labor of other consequential damages, provided that the purchaser notifies management of Mercury Paint Corporation with twenty-four hours of the application of the product.

