

SERIES 7100- IM

INDUSTRIAL MAINTENANCE COATING

ALKYD SEMI-GLOSS FINISH



PRODUCT FEATURES

- Low odor
- Durable
- Excellent gloss retention
- Excellent color retention
- Interior/ Exterior
- Withstands repeated washings

GENERAL PROPERTIES

A heavy duty interior/ exterior, low odor VOC-compliant, semi- gloss alkyd industrial enamel. Dries to a tough finish. For professional and industrial use only.

RECOMMENDED USES

- For use on exterior metal structures and components such as tanks, bridges, fire escapes, pipes, structural steel, hand rails and machinery. For professional or industrial use only. Also recommended for surfaces that require frequent scrubbing with cleaners and scouring agents.

LIMITATIONS

- Do not apply when air and surface temperature are below 45°F

Finish	Semi-gloss
Vehicle Type	Alkyd
Pigment Type	Titanium Dioxide & Light Fast Pigment
Solvent Type	Mineral Spirits
Coating Category	Industrial Maintenance Coating- VOC 250 g/l max
% Solid by Weight	72% minimum
% Solid by Volume	54% minimum
Weight/Per Gallon	10.40 lbs/gal avg
Recommended Dry Film by Coat	1.5 to 2.5 mils per coat
Theoretical Coverage	450-500 sq ft. / gallon
Viscosity @ 77° F	85-95 KU
Dry Time Average	To touch: 2-3 hours To recoat: 16 hours
Application Method	Brush, roller, spray
Shelf Life	2 Years
Packaged	One, two and five gallon pails
Flash Point	105°F
Colors	Stock and custom colors upon request



SURFACE PREPARATION

All surfaces must be dry, thoroughly clean, free of loose paint, rust, grease, oil and all other foreign matter.

APPLICATION CONDITIONS

Temperature: 45°F.-100°F
Relative humidity: up to 85%
Surface temperature: 5°F above dew point

APPLICATION EQUIPMENT

Brush – Good quality china bristle
Roller – Any high quality roller
Spray – Fluid pressure 2,000-2,500 PSI
Tip- 0.15- 0.21 orifice

THINNING / CLEAN UP INSTRUCTIONS

Do not thin. Clean up with xylene or mineral spirits.

ENVIRONMENTAL INFORMATION

Contains no lead, mercury or chromate hazardous compounds. Complies with N.Y., N.J. and other states' requirements for limitation of volatile organic compounds. Meets New York Part 205 architectural surface coatings. Meets criteria for non-photochemical solvents in accordance with New York City Law 49.

Keep out of reach of children.

Safety Data Sheets available upon request.

Keep from freezing.

HEALTH & SAFETY INFORMATION

WARNING! Combustible. Contains mineral spirits and aromatic naphtha. Keep away from heat and open flame. Do not take internally. May irritate eyes and skin. Prolonged breathing of vapors may irritate respiratory tract causing headache, nausea and dizziness. Use only with adequate ventilation. When ventilation is inadequate use respirator. Avoid contact with skin and breathing of vapors or spray mist. In case of eye contact, flush immediately with water. Close container tightly and wash hands properly after each use.

RECOMMENDED SYSTEMS

Ferrous Metal New	Primer: Series 3000 Finish: Series 7100 RI
Ferrous Metal Repainted	Primer: Series 3000 Finish: Series 7100 RI
Galvanized Metal New	Primer: Series 3500 Finish: Series 7100 RI
Galvanized Metal Repainted	Primer: Series 2000 Finish: Series 7100 RI

ACCURACY OF DATA

The technical data presented above are true and accurate as of the date of issuance of this Mercury Paint data sheet and are subject to change without notice. We endeavor to supply all catalog holders with up-to-date catalog pages. Therefore, if the issue date is more than a year old, please inquire whether a new page has since been issued. Please visit www.mercurypaint.com for the newest version of this data sheet.

WARRANTY

This product is warranted only to conform to the analysis and specifications expressed above. No other warranty or guarantee, including its merchantability or suitability for any specific application, is implied. The liability of Mercury Paint Corporation, if any, is limited to replacement of product or refund of purchase price and excludes labor, cost of labor of other consequential damages, provided that the purchaser notifies management of Mercury Paint Corporation with twenty-four hours of the application of the product.

